



## Roundtower Natural Hydraulic Lime (NHL 2)

---

### Properties

- Roundtower NHL 2 is used for internal plastering and externally where the masonry is made up of a soft material.
- It has a high degree of whiteness facilitating the production of quality architectural finishes
- It allows buildings to "breathe", and does not trap moisture in the walls
- Stone and brickwork that is set in lime is easier to re-use / re-cycle
- Lime re-absorbs a proportion of carbon dioxide (CO<sub>2</sub>) emitted during production
- Natural and eco-friendly
- Self healing



### Packaging

- 25-kg paper bags. Pallets of 56/49 bags (1400/1225 kg)

### Advice

- Always take care in excessive weather conditions (rain, sun and frost) and protect the walls
- Always use the minimum quantity of water necessary to form a workable mix. Excess water may be damaging to the physical characteristics of the mortar.
- Work between 8°C and 30°C
- Protect during and after application against low or high temperatures to control setting conditions and avoid any setting issues
- Store bags in dry conditions and off the ground for a maximum of one year after the production date as specified on the bags



## Main characteristics

	Unit	Average values*
<b>Physical properties</b>		
Whiteness	Y	70
Fineness at 90 $\mu$	%	3.8
Fineness at 200 $\mu$	%	0.4
Expansion	mm	0
Bulk density	g/cm <sup>3</sup>	0.592
Real density	g/cm <sup>3</sup>	2.55
Blaine value	cm <sup>2</sup> /g	13097
Free water	%	0.83
<b>Mechanical properties</b>		
Beginning of set	min	987
Mechanical strength at 28 days	MPa	4.69
<b>Chemical properties</b>		
SO <sub>3</sub>	%	1.45
Free lime content	%	41.1

*\*Statistical datas, non contractual*

Complies with the European Standard for building limes (EN 459-1)

## Contact

Roundtower Lime

P : +353 (0) 21 477 6677

P : +44 (0) 1737 581 910

E: [info@roundtowerlime.com](mailto:info@roundtowerlime.com)

Web: [www.roundtowerlime.com](http://www.roundtowerlime.com)

